

STUCCO A28

2K polyester filler putty with liquid catalyst
Designed for finishing fiberglass items.

CHARACTERISTICS:

- Base: polyester unsaturated resin
- Specific gravity: $1,73 \text{ g/cm}^3 \pm 0,05$
- Colour: white
- Appearance: rough, coarse grain.
- Good non-sag consistency
- Good ease of sanding

APPLICATION:

Can be easily applied by knife directly to sanded fibreglass.
Do not apply at temperatures below 5°C.

PREPARATION OF THE MIXTURE:

Catalyse at 1,5-2% with a liquid hardener (MEK peroxide).
Do not apply at temperatures below 5°C.
The final mechanical characteristics may vary depending on the application temperature.

POT-LIFE:

At 20°C: 25 ± 5 minutes

MINIMUM SANDING TIME:

Air-dry at 20°C: 180 minutes

SANDING:

Sequence: P80-P120-P220-P240

OVER PAINTING:

Can be painted over using any type of primer.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.