

COATING 767

DESCRIPTION

Bitumen-free protective coating based on synthetic rubbers in solution, designed for application on car body parts for corrosion and abrasion protection and sound-dampening effect. Dries quickly.

CHARACTERISTICS:

- Base: synthetic rubber solution
- Density: 1,34 g/cm³ ± 0,05
- Dry residue: 73 ± 1%
- Temperature resistance: -30°C/+80°C
- Available colors: black; grey; white

SUBSTRATE PREPARATION:

Thoroughly clean and degrease the surface to be coated using nitro diluent.

APPLICATION:

Ready to use, does not need to be thinned.

Shake well before use.

Apply with Underbody spray gun, pressure 3-5 atm. Depending on pressure, the coating can have a smooth or rough peel.

Application temperature: +5°C to +35°C.

DRYING TIMES:

Dust-dry (20°C): 5 minutes

Complete drying (20°C): 20-30 minutes depending on coat thickness.

OVER PAINTING:

The product can be painted over using solvent-borne basecoat after a short flash-off time, or using waterborne basecoat when dried and sanded.

THEORETICAL COVERAGE: 2-2,5 m²/kg

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.