

S12

2K polyester sprayable filler putty.
Multi-coat application allows to obtain high thicknesses.
Ideal for finishing models. Can be sanded.

CHARACTERISTICS:

- Base: orthophtalic polyester unsaturated resin
- Specific gravity: $1,50 \text{ g/cm}^3 \pm 0,05$
- Colour: light grey
- Appearance: smooth, fine grain.
- Excellent non-sag consistency
- Excellent ease of sanding

APPLICATION:

Can be easily applied with a spray gun directly to:

- Bare sheet metal, well degreased and sanded;
- Old paint, previously sanded with P80;
- Sanded fibreglass.

Do not apply at temperatures below 5°C.

The final mechanical characteristics vary according to the working temperature.

PREPARATION OF THE MIXTURE:

Catalyze at 1.5/2% according to the temperature (2% between 10 and 20°C). Use the appropriate liquid hardener for S-type fillers.

A higher curing rate can be obtained using 1.5/2% MEK peroxide catalyst (polyester resin hardener liquid).

POT-LIFE:

At 20°C: 22 ± 8 minutes

MINIMUM SANDING TIME:

Air-dry at 20°C: 360 minutes

SANDING:

Sequence: P240-P320

OVER PAINTING:

Can be painted over using any type of primer.

The effectiveness of our products is based on practical experiences and research work carried out in our laboratories; nevertheless we accept no liability for work carried out following our instructions being clear that the final result depends in all cases on a series of unforeseeable factors.

* For any information about product codes or packs, please see our catalogue, our price list or contact us.